



## Tech Data Sheet

### Tinted Butyrate Topcoat



#### Description

The Superflite tinted butyrate is the final coating in the butyrate covering process – this is the topcoat color.



#### Components

- Tinted Butyrate Topcoat
- 132 Retarding Thinner



#### Mixing Ratio

Mix 2:1 with the retarding thinner – 2 parts color, 1 part 132.



#### Pot Life @ 77°F

When properly covered at 77° F, the tinted butyrate will maintain a sprayable viscosity for an indefinite period of time.



#### Suitable Substrates

- Superflite fabric



#### Surface Preparation

*For Fabric Surfaces Only:*  
Use after applying the 301 Sprafil.



#### Application

Number of Coats: 2-4  
Application Density: Medium-wet to wet

Flash: 2 hours at 70° F  
Application Conditions: *Minimum Temp* none  
*Max Temp* 85° F  
*Ambient Humidity* 50% or lower



### Equipment Recommendations

---

*For application on fabric:*  
HVLP compressor unit with a high volume nozzle



### Flash/Dry Times

---

Ambient Application (reported at 70° F and 50% humidity)  
Flash Between Coats                      2 hours



### Physical Data

---

Appearance & Odor	various colors, lacquer odor
Vapor Density	Heavier than Air
Evaporation Rate	Slower than Ether
Boiling Point or Range	175-329° F
Flashpoint	22° F



### Safety

---

Before using any Superflite product be sure to read all MSDS, application instructions, and warnings. Always wear a properly fitted air purifying respirator with organic cartridges and a particulate filter or a fresh air supplied respirator (depending on product selection), eye protection, gloves, and protective clothing while exposed to any chemical.



### Warning Statement

---

This product is intended for use by trained professionals only. Use as directed. The data presented herein was determined under our controlled conditions. Since environmental conditions play a large role in performance, variations in the data presented herein may be observed as environmental conditions change. This document does not constitute a warranty or guarantee of any kind. Use at your own risk.